

International Journal Research Publication Analysis

Page: 01-04

EXPERIMENTAL STUDY OF PAVEMENT DESIGN BITUMINOUS USING AS REPLACEMENT OF PLASTIC WASTE

***Anurudh Singh, Dr. Vivek Soni, Arpit Saxena**

¹M.Tech. Scholar, ³Associate Professor

Dept. of Civil Engineering, Radharaman Engineering College, Bhopal (M.P)

Article Received: 05 August 2026

Article Revised: 25 August 2026

Published on: 15 September 2026

***Corresponding Author: Anurudh Singh**

M.Tech. Scholar, Dept. of Civil Engineering, Radharaman Engineering College, Bhopal
(M.P)

DOI: <https://doi-doi.org/101555/ijrpa.5373>

ABSTRACT

Several aspects of asphalt mixtures were addressed using the state of the art laboratory test equipment and technical literature from different information sources. A systematic, simplified design approach was recommended in which asphalt mixtures are designed based on the locking point concept, analytical aggregate gradation method and fundamental mechanistic properties that describe the behavior of asphalt mixtures based on sound engineering principles. In this thesis are use the Marshall method for determining the actual percentage of the waste polythene.

KEYWORDS: - Bitumen, Waste Polythene, Marshall Stability Test, Bitumen, Ductility Test, Penetration Test, Pavement

INTRODUCTION

Road transport in Indian has been developing at a very fast rate in view of various advantages itenjoys. Motor vehicle population is currently witnessing a so appalling that serious economic losses like fuel wastages, delays, congestion, accidents and pollution hazards are posing daunting challenges. Therefore, with the increased traffic planners got realize that there is a need to upgrade India's road system. The new road should be capable of handling the increase in the number of motor vehicles with comfort, speed, and safety. For these massive investments are required to achieve. Bituminous binders are widely used by paving industry. A pavement has different layers. The main constituents of bituminous concrete (BC) are aggregate and bitumen.

Literature Review

Sangita et al. (2011) were over that The Marshall tests of the waste chemical compound changed hydrocarbon concrete (WPMB) mixes, ready through dry method, indicated the optimum waste chemical compound modifier content to be V-E Day (by weight of optimum hydrocarbon content). The waste chemical compound changed hydrocarbon combine containing V-E Day rates showed considerable improvement in numerous mechanical properties of {the combine |the combination |the combo} compared to the standard hydrocarbon concrete mix.

Ahmadinia, E et al. (2011) were over that the most purpose of this analysis is to see the result of incorporating waste plastic bottles (Polyethylene Terephthalate (PET)) on the engineering properties of stone mastic asphalt (SMA) mixture. The meter and mechanical properties of asphalt mixes that embody numerous percentages of PET (0%, 2%, 4%, 6%, V-E Day and 10%) were calculated and assessed with laboratory tests. the suitable quantity of PET was found to be 6 June 1944 by weight of hydrocarbon. The outcomes were statistically analysed and also the determination of the importance at sure confidence limits was performed with the 2 issue variance analysis (ANOVA). Moreover, some studies conducted on synthetic resin changed asphalt mixture have additionally been taken into thought during this paper. The results show that the addition of PET encompasses a vital positive result on the properties of SMA Associate in Nursingd it will promote the re-use of waste product in trade in an environmentally friendly and economical means.

Gawande, A et al. 2012 were over that this review supposed to search out the effective ways in which to reutilize the arduous plastic waste particles as hydrocarbon modifier for versatile pavements. The employment of recycled waste plastic in pavement asphalt represents a valuable outlet for such materials. The employment of changed hydrocarbon with the addition of processed waste plastic of concerning 5-10% by weight of hydrocarbon helps in considerably up the Marshall Stability, strength, fatigue life and different fascinating properties of hydrocarbon concrete combine, ensuing that improves the longevity and pavement performance with marginal saving in hydrocarbon usage. The method is setting friendly, the employment of waste plastics within the manufacture of roads and laminated roofing additionally facilitate to consume great quantity of waste plastics. Thus, these processes ar socially extremely relevant, giving higher infrastructure.

Naskar, et al. (2012) were over that totally different changed hydrocarbon binders are employed in pavement construction for improved sturdiness and for increased performance in resisting cracking and permanent deformation of hydrocarbon layers. Waste plastics, whose disposal could be a matter of concern; are used with success for modifying hydrocarbon. This paper reports the thermo mensuration studies conducted on waste plastic changed hydrocarbon binders. Changed hydrocarbon binders ready victimisation totally different plastic contents (0–7 skyscraper by weight of bitumen) were investigated.

METHODOLOGY

The most serious distresses related to versatile pavement is cracking that happens at intermediate and low temperatures and permanent deformation that happens at high temperatures. These distresses cut back the services lifetime of the pavement and increase the upkeep prices. Optimum bitumen content in any bituminous mix plays a vital role for its stability and durability.

AGGREGATES

Most of the road aggregates are prepared from natural rock. Gravel aggregates are unit tiny rounded stones of various sizes that are unit usually obtained per se from some stream beds. Sand is ok mixture from weathering of rock. The properties of the rock, from that the aggregates are shaped; depend upon the properties of constituent materials and therefore the nature of bond between them. Based on the origin, natural rocks are classified as igneous, sedimentary and metamorphic. Texture are the important factor, it is affecting the property of the rock and the fragments.

BITUMEN

Present or crude bitumen may be a sticky, tar-like sort of crude that is therefore thick and serious that it should be heated or diluted before it'll flow. At temperature, it's very like cold syrup. Refined bitumen is that the residual (bottom) fraction obtained by fractionation of fossil fuel. It's the heaviest fraction and therefore the one with the highest boiling purpose, boiling at 525 °C (977°F).

CONCLUSION

1. Maximum Marshall Stability value is 915 at 5% of polythene content and 5.5 % constant bitumen content.

1. It is watched that the Marshall Stability value is increased at the percentage of 5% and that decreased
2. Marshall Flow value increased with increasing the polythene content Marshall Stability= 915 kg

Bitumen content corresponding to maximum Stability = 5.5 %

Bitumen content (5.5%) and polythene content (5%) corresponding to

- Air voids = 3.75%
- VFB at 5.1 % = 66.95%

For a country like India, where hot temperature prevails in summer in several parts, permanent deformation of bituminous layer is a major concern. This problem can be addressed by adopting courser gradation for wearing course. In the Marshall stability value increases with polyethylene content up to 5% and thereafter decreases. 6.2

REFERENCES

1. Ahmadinia, E et al. (2011). Using waste plastic bottles as additive for stone mastic asphalt. *Materials & Design*, 32(10), pp.4844-4849.
2. Arjita Biswas, Amit Goel, Sandeep Potnis, Performance Evaluation of Sustainable bituminous Plastic roads for Indian conditions, *International Journal of Engineering and Advanced Technology (IJEAT)* ISSN: 2249 – 8958, Volume-9 Issue-1, October 2019, PP-6384-6392
3. Behnood, A., Gharehveran, M.M., Asl, F.G. and Ameri, M., 2015. Effects of copper slag and recycled concrete combination on the residences of CIR mixes with bitumen emulsion, rice husk ash, Portland cement and fly ash. *Construction and Building Materials*, 96, pp.172-180.
4. Bhageerathy K. P, Anu P. Alex, Manju V. S, Raji A. K (2014) “Use of Biomedical Plastic Waste in Bituminous Road Construction” *International Journal of Engineering and Advanced Technology (IJEAT)* ISSN: 2249 – 8958, Volume-3 Issue-6.
5. Chavan, A.J., 2013. Use of plastic waste in bendy pavements. *International Journal of Application or Innovation in Engineering and Management*, 2(4), pp.540-552.
6. Fengchi Xu, Yao Zhao, Kangjian Li, Using Waste Plastics as Asphalt Modifier, College of Civil Engineering, Nanjing Forestry University, Nanjing 210037, China, *Materials*, 110; <https://doi.org/10.3390/ma15010110>, 2022.